Userguide No 023 | March 2012

Chemical Stability of Consumables

Kornelia Ewald, Eppendorf AG, Hamburg, Germany

Abstract

Consumables such as Eppendorf tubes and pipette tips have to withstand the different kinds of stress and strain encountered in everyday laboratory work, e.g. when centrifuging and autoclaving, and at the same time are exposed to chemical reactions. Their level of stability to these effects is, to a large degree, determined by their material and its processing during manufacture. As a leading manufacturer of biotech products, Eppendorf uses PP and PE granulates specifically suited for the laboratory application and manufacturing process of its micro test tubes, Combitips and tips.

Chemical interactions with consumables

Chemicals interact with consumables in a number of different ways. These include:

- The chemical reaction with the polymer, e.g. by oxidation, reaction with the functional group, and by depolymerization.
- Dissolving the synthetic material with a solvent or introducing the solvent into the synthetic material to induce swelling and a change in the material's mechanical properties.
- The formation of tension cracks resulting from mechanical stress and surface-active substances (detergents, oils). The stress can be caused by internal forces (inherent material stress) or as a consequence of an external process (centrifugation).

Potential Applications

In many applications it is necessary to dispense acids, bases, solvents and salt solutions with varying densities, vapor pressures and viscosities; whereby their properties differ considerably from that of water. Such substances influence the chemical resistance of the materials with which contact is made. Prior to using a dispensing system two questions must thus be answered:

- 1. How great are the dispensing errors resulting from the physical properties of the liquids?
- 2. Is the pipette tip or the Combitip tight during dispensing despite the chemical influences and will the pipette or dispenser remain resistant for a protracted period of time?

Chemical Stability

Consumables are generally made of polypropylene (PP) or polyethylene (PE). For both thermoplasts the relevant literature contains extensive information about chemical resistance. It attests a high level of chemical resistance for both PP and PE [1]. According to this reference work, conditional stability is still attributed to a plastic, for example, even though it may be damaged by uninterrupted contact with a chemical for a period of weeks. As meaningful as this data may be for the storage of materials in plastic tubes, it does not reflect conditions prevalent for the much shorter contact times involved with dispensing. Liquids to which PP or PE are only conditionally resistant according to the literature such as inorganic acids and various organic acid solvents such as acetone, diethyl ether, chloroform or toluene can be dispensed without a problem. The prerequisite here is that the contact time is minimized, i.e. the plastic is not used for uninterrupted series pipetting, and the liquid is not additionally heated. As regards the resistance of pipette and dispenser tips, it is a basic rule that the expected dispensing error will increase the longer a consumable is used for the above chemicals. However, it remains surprisingly low for many substances. The following classification can therefore only provide some general information. When in doubt, a test should be carried out. Our information concerning autoclavability (121 °C, 20 min) for Eppendorf consumables should also be taken into account. The greatest degree of safety is obtained by using the disposable tips and tubes only once.

eppendorf

No 023 | Page 2



Eppendorf epT.I.P.S., Tubes and Combitips advanced are also available in Eppendorf Biopur quality, i.e. sterile, free of RNase, DNase and PCR inhibitor, human and bacterial DNA, Pyrogen and ATP. epT.I.P.S., Tubes and Combitips advanced are also available in PCR clean quality, i.e. free of human DNA, DNase, RNase and PCR inhibitor.

Chemical resistance of PP and PE

Chemicals	Concentration	Other names	Tempe	erature	PE*1	PP*2	PC*3	Steam	Density	Viscosity	Remarks
	in %		°C					pressure at	at 20 °C	at 20 °C	
								20 °C (hPa)	(mg/µL)	(mPas)	
Acetaldehyde	40	Ethanal	20	60	03	11	3	1006	0.78		
Acetic acid	25–60	Ethane acid	40	60	1 1	11	0		1.06	1.22	
Acetone	100	Dimethylketone	20	60	23	12	3	246	0.79		
Ammonium hydroxide	30		6	0	1	2	0	483	0.89		
Aniline	100		20	60	1 1	11	3		1.02	4.4	
Benzene	100		20	60	23	23	3		0.88		
Benzine	100		20	60	23	23	2				
Butanol	up to 100	Butyl alcohol	20	60	1 2	12	1		0.81		
Chloroform	100	Trichlormethane	20	60	23	23	3	213	1.47		
Diethyl ether			20	60	23	20	3	587	0.71		
Dimethylformamide	100		20	60	1 2	11	3		0.94		
Dioxane	100		20	60	1 2	22	3		1.03	1.32	
Ethanol	96	Ethyl alcohol	2	0	2	2	1	58	0.8	1.52	
Ethyl acetate	100		20	60	1 2	12	0	98	0.9		
Formaldehyde	40	Methanal	40	60	1 1	11	1				
Formic acid	85	Methanoic acid	20	60	1 1	12	0		1.19	1.4	
Glycerol	each		6	0	1	1	2		1.26	1480	
Hydrochloric acid	37		20	60	1 2	11	2	190	1.18	1.9	
Hydrofluoric acid	up to 40		20	60	1 1	11	3		1.14		Warning! Corrosive!
											Attacks the ceramic
											piston of the pipette.
Isopropanol	each	Isopropyl alcohol	6	0	1	1	2	43	0.78		
Methanol	100	Methyl alcohol	40	60	12	11	0	129	0.79		
Methylene chloride	100	Dichlormethane	20	40	33	23	3	475	1.3		
Nitric acid	65		20	60	33	33	3		1.51	1.77	Pipette must be adjusted
Perchloric acid	70		20	60	13	0	0		1.68		Pipette must be adjusted
Petroleum ether	100		20	60	22	12	2	58			
Phenol	90		20	60	12	11	2		1.07		
Phosphorus acid	80		20	60	1 1	11	0		1.69	30	Pipette must be adjusted
Pyridine	100		20	60	12	22	3	20.5	0.98		
Sodium hydroxide	up to 40		40	60	1 1	11	3		1.43	37	
Sodium hypochlorite			20	60	23	12	0		1.2		
Sulfuric acid	96		20	60	23	23	3		1.84	27	Pipette must be adjusted
Tetrachlormethane	100	Carbon tetrachloride	20	60	33	33	3	120	1.59		Pipette must be adjusted
Tetrahydrofuran	100		20	60	33	23	3	173	0.89		
Toluene	100		20	60	23	23	3		0.87		
Trichloroacetic acid	100	TCA	20	60	23	11	3		1.61		Pipette must be adjusted
Trichlorethene	100		20	60	33	22	3	78	1.46		Pipette must be adjusted

*1 PE = Polyethylene; *2 PP = Polypropylene; *3 PC = Polycarbonate
1 = resistant; the material does not change even after longer contact with the appropriate substance.
2 = conditionally resistant; if the material gets in contact with the substance only for a short time it does not change.
3 = non-resistant; the material already changes after a short contact with the substance.
0 = no existing value.

Source: Carlowitz, B.: Kunststofftabellen. 4. Aufl. München: Hanser, 1995.-ISBN 3-446-17603-9.

No 023 | Page 4

References:

[1] Carlowitz, B.: Kunststofftabellen. 4. Aufl. München: Hanser, 1995.-ISBN 3-446-17603-9.



Your local distributor: www.eppendorf.com/worldwide

Eppendorf AG · 22331 Hamburg · Germany · Tel: +49 40 53801-0 · Fax: +49 40 538 01-556 · E-mail: eppendorf@eppendorf.com Eppendorf North America, Inc. · 102 Motor Parkway · Hauppauge, N.Y. 11788-5178 · USA

Tel: +1 516 334 7500 · Toll free phone: +1 800-645-3050 · Fax: +1 516 334 7506 · E-mail: info@eppendorf.com

Application Support Europe: Tel: +49 1803 666 789 (Preis je nach Tarif im Ausland; 9 ct/min aus dem dt. Festnetz; Mobilfunkhöchstpreis 42 ct/min) E-mail: support@eppendorf.com

> North America: Tel: +1 800 645 3050 · E-mail: techserv@eppendorf.com Asia Pacific: Tel: +60 3 8023 6869 · E-mail: support_asiapacific@eppendorf.com

eppendorf*, epT.I.P.S.*, epDualfilter T.I.P.S.*, Eppendorf Biopur*, Eppendorf Mastertip*, Combitips advanced*, Eppendorf Combitips*, Eppendorf Varitips*, Eppendorf Tubes* and Eppendorf Plates* are registered trademarks of Eppendorf AG. All rights reserved, including graphics and pictures. Copyright © by Eppendorf 2008–2012 Order no. AU023 WW 020/GB4/WEB/0312/NEUH